


EKO 10200185
500MMX10900' | One Sided Cling Machine Film
**TECHNICAL INFORMATION &
TYPICAL PROPERTIES**
>> PRODUCT DESCRIPTION

The next generation in high-performance film with up to 250% or more pre-stretch capacity.

>> PRODUCT SPECIFICATIONS
Film properties

	TYPICAL VALUE (ENGLISH)	TEST METHOD
Tensile Strength at Break MD	5 500 psi	ASTM D882
Tensile Strength at Break TD	4 500 psi	ASTM D882
Tensile Strength at 200% MD	1 900 psi	ASTM D882
Tensile Strength at 200% TD	1 450 psi	ASTM D882
Elongation at Break MD	500%	ASTM D882
Elongation at Break TD	650%	ASTM D882
Elmendorf Tear Strength MD	140 g	ASTM D1922
Elmendorf Tear Strength TD	380 g	ASTM D1922
Dart Impact Strength	180 g	ASTM D1709
Gloss In @45°	69.0%	ASTM D2457
Gloss Out @45°	77.0%	ASTM D2457
Haze	<3.0%	ASTM D1003

Dimensions

	VALUE	TEST METHOD
Film Thickness	10.7 micron	ASTM D4649