

WRAPSODY

FIT 10200268

750MMX8000' | One Sided Cling Machine Film

TECHNICAL INFORMATION & TYPICAL PROPERTIES

>> PRODUCT DESCRIPTION

Improved puncture and wear resistance. Ideal for difficult-to-handle items and perfect for cold environments.

>> APPLICATIONS

High volume | High speed wrapping | One-sided cling required

>> PRODUCT SPECIFICATIONS

Film properties

	TYPICAL VALUE (ENGLISH)	TOLERANCE	TEST METHOD
Tensile Strength at Yield MD	1 350 psi	± 15%	ASTM D882
Tensile Strength at Yield TD	1 250 psi	± 15%	ASTM D882
Tensile Strength at Break MD	6 700 psi	± 15%	ASTM D882
Tensile Strength at Break TD	4 000 psi	± 15%	ASTM D882
Elongation at Break MD	480%	± 15%	ASTM D882
Elongation at Break TD	600%	± 15%	ASTM D882
Protrusion Puncture	10.5 lbs	± 15%	ASTM D5748
Protrusion Puncture Energy	18.6 in-lb	± 15%	ASTM D5748
Elmendorf Tear Strength MD	300 g/mil	± 15%	ASTM D1922
Elmendorf Tear Strength TD	600 g/mil	± 15%	ASTM D1922
Cling – Outside to Inside @ 225%	min 150 g/in	± 15%	ASTM D5458

Dimensions

	VALUE	TOLERANCE
Core ID	3.05 inches	± 0.05 in
Film Thickness	15.2 micron	