

WRAPSODY

CAST 10101538

13.5"X1450' | Cast Hand Film

TECHNICAL INFORMATION & TYPICAL PROPERTIES

>> PRODUCT DESCRIPTION

This clear, glossy film offers enhanced coverage. Facilitates bar code scanning.

>> PRODUCT SPECIFICATIONS

Film properties

	TYPICAL VALUE (ENGLISH)	TEST METHOD
Tensile Strength at Yield MD	5 100 psi	ASTM D882
Tensile Strength at Yield TD	3 900 psi	ASTM D882
Tensile Strength at Break MD	1 500 psi	ASTM D882
Tensile Strength at Break TD	1 300 psi	ASTM D882
Elongation at Break MD	300%	ASTM D882
Elongation at Break TD	700%	ASTM D882
Protrusion Puncture	9.5 lbs	ASTM D5748
Protrusion Puncture Energy	17.6 in-lb	ASTM D5748
Elmendorf Tear Strength MD	40 g/mil	ASTM D1922
Elmendorf Tear Strength TD	850 g/mil	ASTM D1922
Cling – Outside to Inside @ 225%	min 150 g/in	ASTM D5458

Dimensions

	VALUE
Film Thickness	16.5 micron