


**EKO 10200185**
**500MMX10900' | One Sided Cling Machine Film**
**TECHNICAL INFORMATION &  
TYPICAL PROPERTIES**
**>> PRODUCT DESCRIPTION**

The next generation in high-performance film with up to 250% or more pre-stretch capacity.

**>> PRODUCT SPECIFICATIONS**

Clear

**>> PRODUCT SPECIFICATIONS**
**Film properties**

	<b>TYPICAL VALUE (ENGLISH)</b>	<b>TEST METHOD</b>
Tensile Strength at Break MD	5 500 psi	ASTM D882
Tensile Strength at Break TD	4 500 psi	ASTM D882
Tensile Strength at 200% MD	1 900 psi	ASTM D882
Tensile Strength at 200% TD	1 450 psi	ASTM D882
Elongation at Break MD	500%	ASTM D882
Elongation at Break TD	650%	ASTM D882
Elmendorf Tear Strength MD	140 g	ASTM D1922
Elmendorf Tear Strength TD	380 g	ASTM D1922
Dart Impact Strength	180 g	ASTM D1709
Gloss In @45°	69.0%	ASTM D2457
Gloss Out @45°	77.0%	ASTM D2457
Haze	<3.0%	ASTM D1003

**Dimensions**

	<b>VALUE</b>	<b>TEST METHOD</b>
Film Thickness	10.7 micron	ASTM D4649