


**INPAK 10200266**
**750MMX6000' | Cast Machine Film**
**TECHNICAL INFORMATION &  
TYPICAL PROPERTIES**
**>> PRODUCT DESCRIPTION**

With its outstanding holding force, this film is ideal for unstable and irregular packaging.

**>> PRODUCT SPECIFICATIONS**
**Film properties**

	<b>TYPICAL VALUE (ENGLISH)</b>	<b>TOLERANCE</b>	<b>TEST METHOD</b>
Tensile Strength at Yield MD	1 250 psi	± 15%	ASTM D882
Tensile Strength at Yield TD	1 200 psi	± 15%	ASTM D882
Tensile Strength at Break MD	6 900 psi	± 15%	ASTM D882
Tensile Strength at Break TD	4 000 psi	± 15%	ASTM D882
Elongation at Break MD	430%	± 15%	ASTM D882
Elongation at Break TD	600%	± 15%	ASTM D882
Protrusion Puncture	9.5 lbs	± 15%	ASTM D5748
Protrusion Puncture Energy	21.0 in-lb	± 15%	ASTM D5748
Elmendorf Tear Strength MD	330 g/mil	± 15%	ASTM D1922
Elmendorf Tear Strength TD	530 g/mil	± 15%	ASTM D1922
Cling – Outside to Inside @ 225%	min 150 g/in	± 15%	ASTM D5458

**Dimensions**

	<b>VALUE</b>	<b>TOLERANCE</b>
Core ID	3.05 inches	± 0.05 in
Film Thickness	17.75 micron	