

WRAPSODY

CAST 10101852

13.5" x 1450' | Hand Stretch Film

TECHNICAL INFORMATION & TYPICAL PROPERTIES

»» PRODUCT DESCRIPTION

This clear, glossy film offers enhanced coverage. Facilitates bar code scanning.

»» PRODUCT SPECIFICATIONS

Film properties

	TYPICAL VALUE (ENGLISH)	TEST METHOD
Tensile Strength at Yield MD	1 450 psi	ASTM D882
Tensile Strength at Yield TD	1 300 psi	ASTM D882
Tensile Strength at Break MD	5 000 psi	ASTM D882
Tensile Strength at Break TD	3 800 psi	ASTM D882
Elongation at Break MD	320%	ASTM D882
Elongation at Break TD	730%	ASTM D882
Protrusion Puncture	10.0 lbs	ASTM D5748
Protrusion Puncture Energy	19.9 in-lb	ASTM D5748
Elmendorf Tear Strength MD	40 g/mil	ASTM D1922
Elmendorf Tear Strength TD	800 g/mil	ASTM D1922
Cling – Outside to Inside @ 225%	min 150 g/in	ASTM D5458

Dimensions

	VALUE
Film Thickness	19 microns