

**EKO EVO II 10200288****500MM x 10 000' | Machine Stretch Film****TECHNICAL INFORMATION &
TYPICAL PROPERTIES****» PRODUCT DESCRIPTION**

The next generation in high-performance film with high tensile strength and up to 250% or more pre-stretch capacity.

» COLOR

Clear

» PRODUCT SPECIFICATIONS**Film properties**

	TYPICAL VALUE (ENGLISH)	TEST METHOD
Ultimate Tensile	5 270 psi	ASTM D882
Ultimate Tensile	7 310 psi	ASTM D882
Elongation at Break MD	668%	ASTM D882
Elongation at Break TD	786%	ASTM D882
Elmendorf Tear Strength MD	211 g	ASTM D1922
Elmendorf Tear Strength TD	348 g	ASTM D1922
Dart Impact Strength	193 g	ASTM D1709
Gloss @45°	91.0%	ASTM D2457
Haze	1.4%	ASTM D1003

Dimensions

	VALUE
Film Thickness	11.4 microns