

**EKO EVO III 10200289****500MM x 9 000' | Machine Stretch Film****TECHNICAL INFORMATION &
TYPICAL PROPERTIES****» PRODUCT DESCRIPTION**

The next generation in high-performance film with high tensile strength and containment force and up to 250% or more pre-stretch capacity.

» COLOR

Clear

» PRODUCT SPECIFICATIONS**Film properties**

	TYPICAL VALUE (ENGLISH)	TEST METHOD
Ultimate Tensile	5 690 psi	ASTM D882
Ultimate Tensile	7 400 psi	ASTM D882
Elongation at Break MD	697%	ASTM D882
Elongation at Break TD	808%	ASTM D882
Elmendorf Tear Strength MD	290 g	ASTM D1922
Elmendorf Tear Strength TD	415 g	ASTM D1922
Dart Impact Strength	206 g	ASTM D1709
Gloss @45°	91.0%	ASTM D2457
Haze	1.4%	ASTM D1003

Dimensions

	VALUE
Film Thickness	12.7 microns