

WRAPSODY

ORBIT 10200361

10" x 6 000' | Machine Stretch Film

TECHNICAL INFORMATION & TYPICAL PROPERTIES

» PRODUCT DESCRIPTION

Ideal film for horizontal packaging applications, quiet and clear.

» COLOR

Clear

» PRODUCT SPECIFICATIONS

High volume and high-speed wrapping, OSC

Film properties

	TYPICAL VALUE (ENGLISH)	TOLERANCE	TEST METHOD
Tensile Strength at Yield MD	1300 psi	± 15%	ASTM D882
Tensile Strength at Yield TD	1200 psi	± 15%	ASTM D882
Tensile Strength at Break MD	6600 psi	± 15%	ASTM D882
Tensile Strength at Break TD	3900 psi	± 15%	ASTM D882
Elongation at Break MD	510%	± 15%	ASTM D882
Elongation at Break TD	630%	± 15%	ASTM D882
Protrusion Puncture	12.5 lbs	± 15%	ASTM D5748
Protrusion Puncture Energy	24.6 in-lb	± 15%	ASTM D5748
Elmendorf Tear Strength MD	300 g/mil	± 15%	ASTM D1922
Elmendorf Tear Strength TD	600 g/mil	± 15%	ASTM D1922
Cling - Outside to Inside @ 225%	min 150 g/in	± 15%	ASTM D5458

Dimensions

	VALUE	TOLERANCE
Core ID	3.05 inches	± 0.05 in
Film Thickness	20.3 micron	